

PRODUCT DATA BROCHURE

Vinyl Compounds for General Purpose Molding & Extrusion

Our Staff is available to answer questions
and provide technical assistance at
(978) 537-8261

Properties	Durometer "A", INST/15 Sec +/- .03	Specific Gravity +/- .03	Tensile Strength, PSI	100% Modulus PSI	Elongation %	Brittle Point °C	Suggested Stock Temp, °F	Suggested Applications
ASTM	D-2240	D-792	D-412	D-412	D-412	D-746		
G-2100-80	85/80	1.22	2137	1550	325	-25	340-360	Clear for extrusion & molding
G-2100-90	89/84	1.23	2600	1720	300	-20	340-360	Clear for extrusion & molding
G-2163	75/70	1.20	2020	1285	375	-30	330-340	Clear, flexible for profile extrusion
G-2552E	58D	1.25	2800	1800	280	-20	350-360	Clear for profile extrusion
G-3357E	68/62	1.21	1700	1150	375	-37	320-330	General purpose extrusion
G-4157E	60D	1.39	2900	1675	300	-20	330-350	General purpose, satin finish for profile extrusion
G-4285UV	97/90	1.42	3000	1485	250	-25	345-365	UV resistant for profile extrusion
GR-95-071F	84D	1.35	6100	—	—	—	360-375	Clear, rigid for profile extrusion

All compounds are available in Natural, as well as a wide spectrum of colors. Contact S&E Specialty Polymers LLC for color matches. This is merely a sampling of the compounds offered by S&E Specialty Polymers. We encourage you to contact us concerning your specific applications.

140 Leominster-Shirley Road | Gianna Park, P.O. Box 120 | Lunenburg, MA 01462 | **978.537.8261**
admin/exec fax **978.840.4645** | sales/general fax **978.534.8362** | www.sespoly.com

