

“Compounding for the Best”

G-2170

Application: Clear extrusion PVC compound.

PRODUCT SPECIFICATIONS

Property	Units	Value	Test Method
Durometer	Shore A	75/70(±2)	ASTM D2240
Specific Gravity	g/cm ³	1.20 (±2)	ASTM D792
Tensile Strength	psi	2020	ASTM D412
Elongation	%	375	ASTM D412

**Our Staff is available to answer questions and provide technical assistance at
(978) 537-8261**

140 Leominster-Shirley Road | Lunenburg, MA 01462 | 978.537.8261
Sales Fax: 978.534.8362 | General Fax: 978.537.5310 | www.sespoly.com

08/26/2009

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.