

“Compounding for the Best”

GA-1941-AFRO

Application: 105°C PVC insulating compound designed for SJEOO applications.

PRODUCT SPECIFICATIONS

Property	Units	Value	Test Method
Specific Gravity	g/cm ³	1.27(±0.03)	ASTM D792
Durometer	Shore A	84/75(±3)	ASTM D2240
Tensile Strength	psi	2650	ASTM D412
100% Modulus	psi	1400	ASTM D412
Elongation	%	350	ASTM D412
Oxygen Index	%	27	ASTM D2863
Air Oven aged 7 days @ 136°C	°C		
Tensile Retained %	%	86	UL Standard
Elongation Retained %	%	95	UL Standard
Oil Oven aged 7 days @ 60°C	°C		
Tensile Retained %	%	85	UL Standard
Elongation Retained %	%	94	UL Standard

**Our Staff is available to answer questions and provide technical assistance at
(978) 537-8261**

140 Leominster-Shirley Road | Lunenburg, MA 01462 | 978.537.8261
Sales Fax 978.534.8362 | General Fax 978.537.5310 | www.sespoly.com

08/29/2009

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.