

GF-3161PNU

High performance oil, gasoline and chemical resistant soling compound specially formulated for resistance to a broad range of industrial chemicals for extreme hard service usage.

Property	Value	Test Method
Hardness/Durometer Shore A	67/54	ASTM# D-2240
Specific gravity +/-	1.27	ASTM# D-792
Tensile Strength, psi	1460	ASTM# D-412
Elongation %	410	ASTM# D-412

Weight change %

14 days in chicken fat @ room temperature	-7
14 days in ASTM oil#2 @ room temperature	-6
14 days in Wesson oil @ room temperature	-6
14 days in unleaded gasoline	-9

Slip Resistance

ASTM D1894

Varnished wood	Dry	1.85
	Wet	0.80
Vinyl tile	Dry	1.82
	Wet	0.60
Mason tile	Dry	1.01
	Wet	0.74

Suggested stock temperature 330-340°F

The information presented here is, to the best of our knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement of recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.